


NORGIPS S GKFI 12,5 mm type DFH2

NORGIPS®

Fire-resistant plasterboard, impregnated



PRODUCT DESCRIPTION

This fire-resistant plasterboard features tapered, cardboard-laminated longitudinal edges and square transverse edges. The plasterboard gypsum core features an increased density and is glass fibre-reinforced. A hydrophobic agent (paraffin or silicone) is added to the gypsum core of the plasterboard.

Colour - green-coloured cardboard with designations in red.

INTENDED USE

Plasterboard for indoor construction purposes. Designated for interior lining of any kind and for use as a part of dry lining systems applied in rooms with increased humidity, such as bathrooms or kitchens. The relative humidity in such rooms may exceed 70%, but not for longer than 10 hours a day and it must not exceed 85%. The maximum application temperature is 50°C.

The plasterboard is intended for sheathing of partition or curtain walls, wall linings, panelling of suspended ceilings and lining of attics, with the objective to obtain fire-rated partitions (max. up to EI 180).

TECHNICAL PARAMETERS


Type of edge	NORGIPS S (KS)
Reaction-to-fire performance	A2-s1, d0
Flexural strength [N]:	
longitudinal direction	≥550
cross direction	≥210
Gypsum core density [kg/m ³]	≥800
Water vapour diffusion resistance factor [μ]	10
Total water absorption [%]	≤10
Surface water absorption [g/m ²]	220
Thermal conductivity coefficient [λ]	0,25 W/(m*K)



Plasterboards + Profiles + Compound + Accessories = NORGIPS Solution

ADVANTAGES

- **Fire-resistant.** The gypsum core contains a glass fibre-reinforcement that increases its cohesiveness properties when exposed to high temperatures.
- **Impregnated.** Due to waterproofing, the plasterboard features reduced water absorption properties.
- **Edge S.** Tapered longitudinal edges make finishing of the panel joints easier. Due to an appropriate moulding and the use of joint compounds belonging to the Norgips system as well as joint tapes for joint finishing, a joint with a maximum strength can be obtained.



DIMENSIONS AND PACKAGING

Thickness (mm)	Width (mm)	Length (mm)	Quantity per pallet		Weight [kg/m ²]	
			(pcs)	(m ²)	1 m ²	Pallet
12,5	1200	2600	64	199,68	10,1	2017

NOTES FOR GUIDANCE

Use the NORGIPS plasterboards in accordance with the NORGIPS system recommendations. Storage: store the boards on a flat surface, preferably on a pallet. Keep dry. Plasterboard transport on the construction site: keep the butt edge in vertical position when carrying.

ADDITIONAL INFORMATION

Applicable standard: PN-EN 520+A1:2012 Gypsum plasterboards. Definitions, requirements and test methods.

Declaration of Performance: available on the website www.norgips.pl

NORGIPS sp. z o.o.

ul. Krakowiaków 50,
02-255 Warsaw, PL
tel. + 48 605 338 181

www.norgips.eu

The data presented in this leaflet constitutes solely a product description. It represents a general guidance based on our knowledge and experience, not related to specific applications. Since our products are subjected to constant improvements and development, we reserve the

right to change their parameters without prior notice. The data presented herein cannot form a basis for any claims. If you have any questions, please contact the Norgips Technical Department / Norgips Representative.